


PROCESS DETAILS

Process	EPITAXIAL PLANAR
Die Size	26 x 26 MILS
Die Thickness	7.1 MILS \pm 0.6 MILS
Base Bonding Pad Area	5.5 x 5.5 MILS
Emitter Bonding Pad Area	5.5 x 5.5 MILS
Top Side Metalization	Al Si - 17,000Å
Back Side Metalization	Au - 12,000Å

GEOMETRY



R0

BACKSIDE COLLECTOR

GROSS DIE PER 5 INCH WAFER







25,536

PRINCIPAL DEVICE TYPES

MPS455

145 Adams Avenue
Hauppauge, NY 11788 USA
Tel: (631) 435-1110
Fax: (631) 435-1824
www.centalsemi.com

R1 (28 -March 2005)



145 Adams Avenue
Hauppauge, NY 11788 USA
Tel: (631) 435-1110
Fax: (631) 435-1824
www.centalsemi.com

R1 (28 -March 2005)