Analog 4-wire PET-On-Glass Touch Screen Specification


Rol

1. Mechanical Dimensions and Construction

- 1.1 General: Analog Resistive touch screen is laminated by ITO PET to ITO glass.
- 1.2 Construction :

| Item | Description | Material | Remarks |
|------|------------------------------------|----------------------|-----------------------|
| | ITO PET | 0.188mm ITO PET Film | Antiglare coating |
| 1 | (Top layer) | | Surface hardness: 3H |
| | | | Resistance:300~600Ω/□ |
| 2 | ITO Patterned Glass (Bottom layer) | 1.57mm ITO Glass | Resistance:300~600Ω/□ |
| 3 | Tail Base | Kapton | Separated Tail |
| 4 | Tail Coverlay | Kapton | |
| 5 | Connector | AMP compatible | 2,54mm |
| 6 | Top layer circuit | Silver ink | |
| 7 | Bottom layer circuit | Silver ink | |
| 8 | Layer to layer contacted | Silver ink | |
| 9 | Dot spacer | UV Cure ink | |
| 10 | Isolation Layer | Isolation Adhesive | |

Touch screen side view:



| | Changes that contribute to technical improvement are subject to alternations | | | | | | | | | | |
|----|--|-------|------|---------|------------------------------------|------------|---|---------|---------------------------------------|--------|--------------|
| | | | | 2005 | Datum | Name | | | | | |
| | | | | Bearb. | 04.11. | Maurer | TOUCHSCREEN | | | | |
| | | | | Gepr. | 04.11. | Maurer | | 8, | 48", | 4-Wir | е |
| | | | | Vert. | | | AMT-09530-01 SPECIFICATIONS OF ANALOG RESISTIVE PET-ON-GLASS TOUCH SCREEN | | | | |
| | | | | ED∖ | -Datas | sheet | | | | | OG RESISTIVE |
| | | | | | | | | | | | SCREEN |
| | | | | don't d | don't change manually Manufactured | | | ired by | red by Apex Material Technology Corp. | | |
| | | | | - | | | | н | 107 | 70.042 | 22 |
| Zu | Änd. | Datum | Name | | D 7934 | 46 Endinge | en | pag | e 1 | of 5 | Index: - |

RoHS

1.3 Input Method and Activation Force

| Input Method | Average Activation Force |
|----------------------------|--------------------------|
| 1.6mm dia. Delrin stylus | $0.1 \sim 0.7 N$ |
| 16mm dia. Silicon "finger" | $0,1 \sim 0,8 \; { m N}$ |

2. Typical Optical Characteristics

| 2.1 | Visible Light Transmission: | > 80% |
|-----|-----------------------------|-------|
| 2.2 | Haze: | < 13% |

3. Electrical Specifications

| 3.1 | Operating Voltage: | 5.5V or less |
|-----|---------------------------|---|
| 3.2 | Contact current: | 20mA (maximum) |
| 3.3 | Circuit close resistance: | $X : 400 - 1000\Omega; Y : 200 - 650\Omega$ |
| 3.4 | Circuit open resistance: | $> 10 M\Omega$ at 25VDC |
| 3.5 | Contact bounce: | < 10ms |
| 3.6 | Linear Test : | < 1.5 % |
| 3.7 | Capacitance: | 100nF(maximum) |

4. Linearity


4.1 Linear Test Specification

| Direction X: <1.5 % | |
|---------------------|--|
| Direction Y: <1.5 % | |

4.2 Line Test Circuit for Y Coordinate

Add 5V between Y1 and Y2 touch the point C0R0 to C9R9 separately, and measure the voltage from X1 as the following drawing.

| | Changes that contribute to technical improvement are subject to alternations | | | | | | | | | | |
|----|--|-------|------|---------|-----------------------|--------|---|--|----------|-------------|---|
| | | | | 2005 | Datum | Name | | | | | |
| | | | | Bearb. | 04.11. | Maurer | TOUCHSCREEN | | | | |
| | | | | Gepr. | 04.11. | Maurer | 8,48", 4-Wire AMT-09530-01 | | | | |
| | | | | Vert. | | | | | | | |
| | | | | ED\ | /-Datas | sheet | SPECIFICATIONS OF ANALOG RESISTIVE PET-ON-GLASS TOUCH SCREEN | | | G RESISTIVE | |
| | | | | | | | | | | SCREEN | |
| | | | | don't d | don't change manually | | | Manufactured by Apex Material Technology Corp. | | | |
| | | | | _ | 1.1. TOXA | | | н | 1070. | 0422 | 2 |
| Zu | Änd. | Datum | Name | - | en | pag | e 2 of | 5 | Index: - | | |





5. Environment Specification

| 5.1 | Operating Temperature | - $10^{\circ} \text{ C} \sim +60^{\circ} \text{ C}$ | Humidity less than 90% RH |
|-----|-----------------------|---|---------------------------|
| 5.2 | Storage Temperature | - 40° C \sim + 80° C | at Ambient Humidity |

6. Reliability Test

6.1 Exposure to high temperature Touch panel is put into a test machine at the condition of 80°C for 120 hours. Then it is left at the room temperature for 24 hours or more. The measurement must satisfy the following:

- Circuit close resistance: as Sec. 3.3
- Circuit open resistance: as Sec. 3.4
- Contact bounce: as Sec. 3.5
- Linearity test: as Sec. 3.6

6.2 Exposure to low temperature Touch panel is put into a test machine at the condition of -40°C for 120 hours. Then it is left at the room temperature for 24 hours or more. The measurement must satisfy the following:

- Circuit close resistance: as Sec. 3.3
- Circuit open resistance: as Sec. 3.4
- Contact bounce: as Sec. 3.5
- Linearity test: as Sec. 3.6

6.3 Exposure to constant temperature and humidity

Touch panel is put into a test machine at the condition of 60°C, 90%RH for 120 hours. Then it is left at the room temperature for 24 hours or more. The measurement must satisfy the following:

- Circuit close resistance: as Sec. 3.3
- Circuit open resistance: as Sec. 3.4
- Contact bounce: as Sec. 3.5
- Linearity test: as Sec. 3.6

6.4 Thermal Shock

Touch panel is put into a test machine at the condition of -40° C for 30 minutes, and then 80°C for 30 minutes. The process is repeated by 10 cycles. Then it is left at the room temperature for 24 hours or more. The measurement must satisfy the following:

- Circuit close resistance: as Sec. 3.3
- Circuit open resistance: as Sec. 3.4
- Contact bounce: as Sec. 3.5
- Linearity test: as Sec. 3.6

| | Changes that contribute to technical improvement are subject to alternations | | | | | | | | | | |
|----|--|-------|------|-----------------------|--------|-----------|--|----------------------|--|--|--|
| | | | | 2005 | Datum | Name | | | | | |
| | | | | Bearb. | 04.11. | Maurer | TOUCHSCREEN | | | | |
| | | | | Gepr. | 04.11. | Maurer | | 8,48", 4-Wire | | | |
| | | | | Vert. | | | | AMT-09530-01 | | | |
| | | | | EDV | -Datas | heet | SPECIFICATIONS OF ANALOG RESISTIVE | | | | |
| | | | | | | | PET-ON-GLASS TOUCH SCREEN | | | | |
| | | | | don't change manually | | | Manufactured by Apex Material Technology Corp. | | | | |
| | | | | | | CHUR | 100 () 101 () 100 () 101 () 100 () | H 1070.0422 | | | |
| Zu | Änd. | Datum | Name | | D 7934 | 46 Ending | en | page 4 of 5 Index: - | | | |



7. Durability test:

7.1 Finger touches

Touch panel is hit 10 millions times with a silicone rubber of R8 finger, hitting rate is by 250g at 2 times per second. The measurement must satisfy the following:

- Circuit close resistance: as Sec. 3.3
- Circuit open resistance: as Sec. 3.4
- Contact bounce: as Sec. 3.5
- Linearity test: as Sec. 3.6

7.2 Stylus writing

Touch panel is drawn by R0.8 Derlin stylus pen, at 250g forces, repeat one inch by 100K times. The measurement must satisfy the following:

- Circuit close resistance: as Sec. 3.3
- Circuit open resistance: as Sec. 3.4
- Contact bounce: as Sec. 3.5
- Linearity test: as Sec. 3.6

8. Optical Performance

- 8.1 Optical inspection method and optical defect standards refer to document. A001-2 Touch Screen Optical Quality Standard.
- 8.2 Outside to Viewing Area : any optical defected in this area need to be ignored if no effected to touch screen function.
- 8.3 Silver Bus Pattern defect : Voids in traces to be less than 50% of the trace width.
 - 8.3.1 Silver Bus Pattern gap: >0.1mm
 - 8.3.2 Silver Bus and Active area gap: No silver ink may project beyond the viewing area.
- 8.4 Glass defects such as edge chips and scratches refer to A001-2, Touch Screen Optical Quality Standard.
- 8.5 Others

Always store the touch screen in its original shipping container under normal conditions (20~25°C, 65% RH)

| Changes that contribute to technical improvement are subject to alternations | | | | | | | | | | |
|--|------|-------|------|-----------------------|-------------------|-----------|--|----------------------------|--|--|
| | | | | 2005 | Datum | Name | | | | |
| | | | | Bearb. | 04.11. | Maurer | - | TOUCHSCREEN | | |
| | | | | Gepr. | 04.11. | Maurer | | 8,48", 4-Wire | | |
| | | | | Vert. | | | | AMT-09530-01 | | |
| | | | | EDV | '-Datas | heet | SPECIFICA | ATIONS OF ANALOG RESISTIVE | | |
| | | | | | | | PET-0 | ON-GLASS TOUCH SCREEN | | |
| | | | | don't change manually | | | Manufactured by Apex Material Technology Corp. | | | |
| | | | | | | | TER | | | |
| | | | | | 1.1 TAKA - 7.1997 | ONIC COM | | H 1070.0422 | | |
| | | | | | | | | | | |
| Zu | Änd. | Datum | Name | | D 7934 | 16 Ending | en | page 5 of 5 Index: - | | |